



**Centro Tessile Serico Sostenibile Srl**  
 via Castelnuovo, 3 - 22100 Como Italia  
 Pho +39 031 331211  
 P. IVA - C.F. 03900470133  
 mailbox@textilecomo.com  
 www.textilecomo.com



00041

Test Report No.:	<b>2504114-001</b>	Customer Code 05485
Date Test Report	<b>01-ago-25</b>	Dear:
Acceptance:	<b>2504114</b>	<b>MARIO SIRTORI SPA</b>
Arrival date sample	<b>23-lug-25</b>	via Papa Giovanni XXIII 10
Start date test	<b>23-lug-25</b>	23845 COSTA MASNAGA (LC) Italia
End date test	<b>01-ago-25</b>	C.a. sig.ra Laura Misseri
References:		Phone: +39 031 879632
Sampling Mode:	Sampling by Customer *	

[C] Item:	<b>SMILLA STRETCH - SMILLA STRETCH PLUS</b>
[C] Declared Composition:	<b>32% PC - 19% CO - 17% VI - 8% LI - 7% WP - 7% WV - 6% PL - 3% PA - 1% EA</b>
[C] End use:	<b>furnishing</b>
[C] Typology:	<b>fabric</b>
Return:	<b>no requested</b>

### Test Results

Test	Method	U.M.	Result
<b>15066 UPHOLSTERY FURNITURE COMPONENTS: ASSESSMENT OF THE IGNITABILITY BY SMOULDERING CIGARETTE</b>	<b>UNI EN 1021-1:2014</b>		.
<b>Start date test</b>	31/07/2025		
<b>End date test</b>	01/08/2025		
<b>Instrument:</b> Small Test Rig and burner			
Test carried out on			Cover fabric
Pretreatment carried out			None
Conditioning of sample			23 ± 2 °C, 50 ± 5 % r.h.
Testing temperature and r.h.			20°C - 61% r.h.
Ignition source			source 0 (SMOULDERING CIGARETTE)
<b>TEST RESULT</b>			<b>SAMPLE PASSES THE TEST: NON IGNITION</b>
Deviations from the method			None
Annex n.			1F
Details of the test results related to each specimen can be seen in the annex of this test report.			

(\*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



**Centro Tessile Serico Sostenibile Srl**  
via Castelnuovo, 3 - 22100 Como Italia  
Pho +39 031 331211  
P. IVA - C.F. 03900470133  
mailbox@textilecomo.com  
www.textilecomo.com



00041

Test Report No.: **2504114-001**

Test	Method	U.M.	Result
------	--------	------	--------

**The Laboratory Manager**

Fausto Albonico

-----  
**END OF REPORT**  
-----

(\*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.