

TEST REPORT

Report nr.: **2001033-003**

Report date: **05-mar-20**

Acceptance code: **2001033**

Acceptance date: **12-feb-20**

Start test date: **12-feb-20**

End test date: **05-mar-20**

References: ---

Customer code: 5485

To:
MARIO SIRTORI SPA
via Papa Giovanni XXIII 10
23845 COSTA MASNAGA (LC)
Italia

To the attention of:

sig. Sergio Sala Crist

Tel.nr: +39 031 879632

Fax.nr.: +39 031 855397

Sampling by customer

Article description:

Declared composition:

End use:

Typology:

Return:

SIESTA
100% Polypropylene
Furnishing
Fabric
No requested

The results reported herein refer exclusively to the tested sample as received and do not involve any product approval by Centro Tessile Serico. This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory. The informations as Article Description, Declared Composition and Tipology listed above are data supplied by the Customer for which this Laboratory declines any responsibility.

| TEST | M.U. | RESULTS |
|--|-------------------------|-------------|
| 14203 TENSILE STRENGTH - MAXIMUM FORCE AND ELONGATION AT MAXIMUM FORCE USING THE STRIP METHOD | | |
| Method: | UNI EN ISO 13934-1:2013 | |
| Instrument: | CRE Dynamometer | |
| Date of test: | | 21702/2020 |
| Gauge length | mm | 200 |
| Elongation speed used | mm/min | 100 |
| Pretension applied | N | 5 |
| Specimens condition | | Conditioned |
| Number of specimens for each direction | n. | 5 |
| WARP - maximum force - average | N | 1933 |
| WARP - elongation to max. force - average | % | 63.0 |
| WEFT - maximum force - average | N | 2020 |
| WEFT - elongation to max. force - average | % | 45.0 |
| Number of specimens rejected: | nr. | 0 |
| Deviation from procedure | | - |

(*) = the tests marked with asterisk are not accredited by Accredia.



Centro Tessile Serico Spa consortile
Via Castelnuovo, 3 - 22100 Como, Italia
Tel. +39 031 331211-120 Fax +39 031 3312180
Amministrazione/Contabilità
Tel. +39 0313312102-154
P.IVA - C.F. 02381270137
Capitale sociale euro 552.693,18 i.v.
mailbox@textilecomo.com
www.textilecomo.com



LAB N° 0045 L

Report nr.

2001033-003

TEST

M.U.

RESULTS

----- **END OF TEST REPORT** -----

Technical Head

Enrica Baldini

(*) = the tests marked with asterisk are not accredited by Accredia.