



Centro Tessile Serico Sostenibile Srl
via Castelnuovo, 3 - 22100 Como Italia
Pho +39 031 3312111/120
P. IVA - C.F. 03900470133
mailbox@textilecomo.com
www.textilecomo.com



00041

Test Report No.:	2602864-003	
Date Test Report	12-giu-26	Customer Code 05485
Acceptance:	2602864	Dear:
Arrival date sample	14-mag-26	MARIO SIRTORI SPA
Start date test	14-mag-26	via Papa Giovanni XXIII 10
End date test	29-mag-26	23845 COSTA MASNAGA (LC) Italia
References:		C.a. Ivan Giusti
		Phone: +39 031 879632
Sampling Mode:	Sampling by Customer *	
[C] Item:	SYD	
[C] Declared Composition:	64% WO - 26% PC - 10% PL	
[C] End use:	furnishing	
[C] Typology:	fabric	
Return:	no requested	

Test Results

Test	Method	U.M.	Result
14443 SLIPPAGE RESISTANCE OF YARNS AT A SEAM - fixed load	UNI EN ISO 13936-2:2004		.
Start date test	28/05/2026		
End date test	29/05/2026		
Instrument:	ALPA Digital Caliper		
Instrument:	CRE Dynamometer Titan 5		
FURNISHING:			
Sewing thread :	100% polyester, Linear density 74 tex		
Plain lockstitch type n.301 (ISO 4915:1991)			
Needle: number metric 110			
Stitches/100 mm: 32 ± 2			
Date of test			29/05/2026
Force applied		N	180
WARP over WEFT - seam opening		mm	3
WEFT over WARP - seam opening		mm	2
Number of specimens for each direction		No.	5
Comments			.

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



Centro Tessile Serico Sostenibile Srl
via Castelnuovo, 3 - 22100 Como Italia
Pho +39 031 3312111/120
P. IVA - C.F. 03900470133
mailbox@textilecomo.com
www.textilecomo.com



00041

Test Report No.: **2602864-003**

Test	Method	U.M.	Result
------	--------	------	--------

The Laboratory Manager

Fausto Albonico

END OF REPORT

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.