



Centro Tessile Serico Sostenibile Srl
via Castelnuovo, 3 - 22100 Como Italia
Pho +39 031 3312111/120 Fax: +39 0313312149
Amministrazione/Contabilità +39 031 3312102-154
P. IVA - C.F. 003900470133
Capitale sociale euro 600000,00 iv
mailbox@textilecomo.com
www.textilecomo.com



LAB N° 0045 L

Test Report No.:	2500731-001	
Date Test Report	17-feb-25	Customer Code 05485
Acceptance:	2500731	Dear:
Arrival date sample	10-feb-25	MARIO SIRTORI SPA
Start date test	10-feb-25	via Papa Giovanni XXIII 10
End date test	17-feb-25	23845 COSTA MASNAGA (LC) Italia
References:		C.a. Ivan Giusti
		Phone: +39 031 879632
Sampling Mode:	Sampling by Customer *	
[C] Item:	ROXANA CS 01	
[C] Declared Composition:	100% Trevira CS	
[C] End use:	furnishing	
[C] Typology:	velvet	
Return:	no requested	

Test Results

Test	Method	U.M.	Result
25165 WASHING TREATMENTS	UNI EN ISO 6330:2022		.
Start date test	12/02/2025		
End date test	13/02/2025		
Instrument: WASHING-MACHINE ELECTROLUX WASCATOR mod. FOM 71 CLS			
Typology of washing machine used: Type A			
Programme of washing: 3N - normal agitation			
Test Temperature: 30°C			
Drying procedure: type C - Flat dry			
Detergent used: ECE (ref.A) without optical brightener - Sodium Perborated - TAED			
Total air-dry- mass (specimens and ballast): 2,0 kg			
Type of ballast used: Type III (polyester)			
Number of washings performed: 01			
THE SAMPLE, TREATED AS ABOVE DESCRIBED, HAS BEEN SUBMITTED TO NEXT TEST of CURTAINS AND DRAPES: IGNITABILITY OF VERTICALLY ORIENTED SPECIMENS.			
15386 CURTAINS AND DRAPES:	UNI EN 1101:2006		.
IGNITABILITY OF VERTICALLY ORIENTED SPECIMENS			
Start date test	14/02/2025		
End date test	17/02/2025		
Instrument: Rhoburn Tester			
Pretreatment carried out			N. 1 WASHING AT 30°C
Conditioning of sample			20±2°C - 65±4% U.R
Testing temperature and r.h.			18°C - 51% R.H
Tested sample surface:			Face
Dimension of specimens:	mm		80x200
Type of gas used:			Propane

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.

Test Report No.: **2500731-001**

Test	Method	U.M.	Result
Type of ignition used:			From the edge
MEAN IGNITION TIME			Not detectable
SAMPLE DOES NOT BURN AT 20s OF APPLICATION TIME OF THE FLAME			
Deviations from the method			None
Annex n.			1F
Details of the test results related to each specimen can be seen in the annex of this test report.			
25165 WASHING TREATMENTS	UNI EN ISO 6330:2022		.
Start date test	12/02/2025		
End date test	14/02/2025		
Instrument: WASHING-MACHINE ELECTROLUX WASCATOR mod. FOM 71 CLS			
Typology of washing machine used: Type A			
Programme of washing: 3N - normal agitation			
Test Temperature: 30°C			
Drying procedure: type C - Flat dry			
Detergent used: ECE (ref.A) without optical brightener - Sodium Perborated - TAED			
Total air-dry- mass (specimens and ballast): 2,0 kg			
Type of ballast used: Type III (polyester)			
Number of washings performed: 12			
THE SAMPLE, TREATED AS ABOVE DESCRIBED, HAS BEEN SUBMITTED TO NEXT TEST of BURNING BEHAVIOUR - CURTAINS AND DRAPES - Measurement of flame spread of vertically oriented specimens with large ignition source.			
15676 BURNING BEHAVIOUR - CURTAINS AND DRAPES - Measurement of flame spread of vertically oriented specimens with large ignition source	UNI EN 13772:2011		.
Start date test	14/02/2025		
End date test	17/02/2025		
Instrument: Rhoburn Tester			
Conditioning of sample			20±2°C - 65±4% U.R
Testing temperature and r.h.			18°C - 51% r.h
TEST ON SAMPLE IN ITS ORIGINAL STATE:			
- severing of marker threads	-		Not detectable
Evidence of flaming debris	-		Not detectable
TEST ON REFURBISHED SAMPLE:			
- severing of marker threads	-		Not detectable
Evidence of flaming debris	-		Not detectable
Deviations from the method			None
Annex n.			2F
Details of the test results related to each specimen can be seen in the annex of this test report.			

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



Centro Tessile Serico Sostenibile Srl
via Castelnuovo, 3 - 22100 Como Italia
Pho +39 031 3312111/120 Fax: +39 0313312149
Amministrazione/Contabilità +39 031 3312102-154
P. IVA - C.F. 003900470133
Capitale sociale euro 600000,00 iv
mailbox@textilecomo.com



LAB N° 0045 L

Test Report No.: **2500731-001**

Test	Method	U.M.	Result
15986 TEXTILES AND TEXTILE PRODUCTS - BURNING BEHAVIOUR - CURTAINS AND DRAPES - CLASSIFICATION SCHEME	EN 13773:2004		.
The fabric tested according to standards UNI EN 1101: 2006 "Textiles and textile products. Burning behaviour. Curtains and drapes. Detailed procedure to determine the ignitability of vertically oriented specimens (small flame)" and UNI EN 13772: 2011 "Textiles and textile products. Burning behaviour. Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source"			
MEETS THE REQUIREMENTS OF CLASS 1 according to the UNI EN 13773: 2004 "Textiles and textile products - Burning behavior - Curtains and drapes - Classification scheme"			

The Laboratory Manager

Fausto Albonico

END OF REPORT

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



Centro Tessile Serico Sostenibile Srl
Via Castelnuovo, 3 – 22100 Como Italia
Tel. +39 031331211 Fax +39 0313312149
Amministrazione/Contabilità +39 0313312102-154
P.IVA – C.F. 03900470133
Capitale sociale euro 600.000,00 iv
mailbox@textilecomo.com
www.textilecomo.com



LAB N° 0045 L

Allegato n. 1F al rapporto di prova n. / Annex n. 1F to test report n. 2500731-001

DETTAGLIO DEI RISULTATI DI PROVA
DETAILS OF TEST RESULTS

Prova eseguita in conformità a UNI EN 1101:2006

Comportamento al fuoco - Tende e tendaggi - Procedimento dettagliato per determinare l'inflammabilità di provette verticali (piccola fiamma)

Test executed according to UNI EN 1101:2006

Burning behaviour – Curtains and drapes - Detailed procedure to determine the ignitability of vertically oriented specimens (small flame)

Direzione / Direction: ORDITO /WARP

N. test	Applicazione fiamma (s) Flame application time (s)	Risultato Result
1	1	NI
2	2	NI
3	3	NI
4	4	NI
5	5	NI
6	10	NI

I = accensione / ignition N.I. = non accensione / not ignition

N. test	Applicazione fiamma (s) Flame application time (s)	Risultato Result
7	15	NI
8	20	NI
9	20	NI
10	20	NI
11	20	NI
12	20	NI

Direzione / Direction: TRAMA /WEFT

N. test	Applicazione fiamma (s) Flame application time (s)	Risultato Result
1	1	NI
2	2	NI
3	3	NI
4	4	NI
5	5	NI
6	10	NI

I = accensione / ignition N.I. = non accensione / not ignition

N. test	Applicazione fiamma (s) Flame application time (s)	Risultato Result
7	15	NI
8	20	NI
9	20	NI
10	20	NI
11	20	NI
12	20	NI

Riepilogo risultati ORDITO / Summary of results WARP:

Applicazione fiamma (s) Flame application time (s)	Numero casi di Accensione Number Ignition	Numero casi di Non Accensione Number Not Ignition
From 1 to 20s	0	12

Tempo medio di accensione ORDITO: non rilevabile – il tessuto fonde al momento dell'applicazione della fiamma

Mean time of ignition - WARP: not detectable – sample melts at the application of flame moment

Riepilogo risultati TRAMA / Summary of results WEFT:

Applicazione fiamma (s) Flame application time (s)	Numero casi di Accensione Number Ignition	Numero casi di Non Accensione Number Not Ignition
From 1 to 20s	0	12

Tempo medio di accensione TRAMA: non rilevabile – il tessuto fonde al momento dell'applicazione della fiamma

Mean time of ignition - WEFT: not detectable – sample melts at the application of flame moment

MANCATA ACCENSIONE DEL CAMPIONE IN 20s DI APPLICAZIONE DI FIAMMA
SAMPLE DOESN'T BURN AT 20 s OF APPLICATION TIME OF THE FLAME



Centro Tessile Serico Sostenibile Srl
Via Castelnuovo, 3 – 22100 Como Italia
Tel. +39 031331211 Fax +39 0313312149
Amministrazione/Contabilità +39 0313312102-154
P.IVA – C.F. 03900470133
Capitale sociale euro 600.000,00 iv
mailbox@textilecomo.com
www.textilecomo.com



LAB N° 0045 L

Allegato n. 1F al rapporto di prova n. / Annex n. 1F to test report n. 2500731-001

Nota ITA:

Il tempo massimo di applicazione della fiamma previsto dalla norma è di 20s.

I tessuti che non bruciano in queste condizioni normalmente non bruciano neppure con applicazioni più prolungate di fiamma.

Il test si conclude non appena siano stati registrati almeno: 5 casi di accensione e 5 casi di non accensione OPPURE 5 casi di accensione a 1 s di applicazione della fiamma OPPURE 5 casi di non accensione a 20 s di applicazione della fiamma.

I test preliminari effettuati sia sul lato dritto che sul lato rovescio del tessuto (senso ordito e trama) non hanno evidenziato caratteristiche di infiammabilità diverse

Modalità di calcolo del tempo medio di accensione

Calcolare la media matematica dei tempi relativi all'evento (accensione o non accensione) meno ricorrente.

Sommare 0,5 secondi nel caso in cui il tempo medio sia stato calcolato utilizzando i tempi di NON Accensione. Arrotondare al secondo.

Sottrarre 0,5 secondi nel caso in cui il tempo medio sia stato calcolato utilizzando i tempi di Accensione. Arrotondare al secondo.

Note ING:

The maximum flame application time in according to the test is 20s.

Fabrics that don't burn in these conditions normally don't burn even with flame application time >20 s.

Test stops when: there are at least five instances of ignition and 5 of non-ignition OR there are at least 5 instances of ignition at 1s application of flame OR there are at least 5 instances of non-ignition at 20 s application of flame.

The preliminary tests carried out both on the face and on back side of the fabric (warp and weft direction) revealed no different flammability characteristics.

Calculation of the mean ignition time

Calculate the mean of the recorded times for ignition or not-ignition, whichever has occurred least (example: if the NON IGNITION TIME is the less frequent event, the mean of NON IGNITION events has been calculated) . If the data relate to non-ignition, add 0,5s; if it relates to ignition, subtract 0,5s. Round this result to the nearest second and report as the mean ignition time for the orientation tested.

L'incertezza estesa attribuita dal Laboratorio alle misure di tempo è pari a 3,2 s.

La probabilità che i criteri di osservazione indicati corrispondano al vero è pari al 90%. L'incertezza estesa è ottenuta moltiplicando l'incertezza tipo composta per un fattore di copertura $K=2$, che per una distribuzione normale porta ad un livello di confidenza approssimativamente del 95%

The expanded uncertainty given by the Laboratory at the time of the phenomena of combustion is equal to 3,2 s.

The probability that the criteria represent the truth observation is equal to 90%. The expanded uncertainty is calculated by multiplying the combined standard uncertainty for a coverage factor $k = 2$, which for a normal distribution leads to a confidence level of approximately 95%.

Il Responsabile Laboratorio
The Laboratory Manager
Fausto Albonico

Allegato n. 2F al rapporto di prova n. / Annex n. 2F to test report n. 2500731-001

DETTAGLIO DEI RISULTATI DI PROVA
DETAILS OF TEST RESULTS

Prova eseguita in conformità a UNI EN 13772:2011

Tessili e prodotti tessili – Comportamento al fuoco – Tende e tendaggi

Misurazione della propagazione della fiamma di provini orientati verticalmente sottoposti all'azione di una grande sorgente di accensione

Test executed according to UNI EN 13772:2011

Textiles and textile products – Burning behaviour – Curtains and drapes

Measurement of flame spread of vertically oriented with large ignition source

CAMPIONE TAL QUALE / SAMPLE IN ITS ORIGINAL STATE

Direzione / Direction	ORDITO / WARP				TRAMA/WEFT			
Osservazioni / Observations								
Lato / Face	Dritto Face	Rovescio Back	Dritto Face	Dritto Face	Dritto Face	Rovescio Back	Dritto Face	Dritto Face
Rottura primo filo di riferimento (SI/NO) Severance of the first marker thread (YES/NO)	NO	NO	NO	NO	NO	NO	NO	NO
Rottura secondo filo di riferimento (SI/NO) Severance of the second marker thread (YES/NO)	NO	NO	NO	NO	NO	NO	NO	NO
Rottura terzo filo di riferimento (SI/NO) Severance of the third marker thread (YES/NO)	NO	NO	NO	NO	NO	NO	NO	NO
Tempo rottura terzo filo di riferimento (s) Time to severance of the third marker thread (s)	-	-	-	-	-	-	-	-
Caduta residui infiammati (SI/NO) Flaming debris (YES/NO)	NO	NO	NO	NO	NO	NO	NO	NO
Danneggiamento verticale (mm) Vertical damage (mm)	82	75	73	75	92	80	72	81

CAMPIONE LAVATO 12 volte a 30 °C / SAMPLE WASHED 12 times at 30°C

Direzione / Direction	ORDITO / WARP				TRAMA/WEFT			
Osservazioni / Observations								
Lato / Face	Dritto Face	Rovescio Back	Dritto Face	Dritto Face	Dritto Face	Rovescio Back	Dritto Face	Dritto Face
Rottura primo filo di riferimento (SI/NO) Severance of the first marker thread (YES/NO)	NO	NO	NO	NO	NO	NO	NO	NO
Rottura secondo filo di riferimento (SI/NO) Severance of the second marker thread (YES/NO)	NO	NO	NO	NO	NO	NO	NO	NO
Rottura terzo filo di riferimento (SI/NO) Severance of the third marker thread (YES/NO)	NO	NO	NO	NO	NO	NO	NO	NO
Tempo rottura terzo filo di riferimento (s) Time to severance of the third marker thread (s)	-	-	-	-	-	-	-	-
Caduta residui infiammati (SI/NO) Flaming debris (YES/NO)	NO	NO	NO	NO	NO	NO	NO	NO
Danneggiamento verticale (mm) Vertical damage (mm)	60	53	58	60	73	50	55	64



Centro Tessile Serico Sostenibile Srl
Via Castelnuovo, 3 – 22100 Como Italia
Tel. +39 031331211 Fax +39 0313312149
Amministrazione/Contabilità +39 0313312102-154
P.IVA – C.F. 03900470133
Capitale sociale euro 600.000,00 iv
mailbox@textilecomo.com
www.textilecomo.com



LAB N° 0045 L

Allegato n. 2F al rapporto di prova n. / Annex n. 2F to test report n. 2500731-001

Nessuna rottura del primo filo di riferimento / No severance of first marker thread

Nessuna caduta di detriti infiammati / No flaming debris

L'incertezza estesa attribuita dal Laboratorio alle misure di tempo è pari a 3,2 s. La probabilità che i criteri di osservazione indicati corrispondano al vero è pari al 90%. L'incertezza estesa è ottenuta moltiplicando l'incertezza tipo composta per un fattore di copertura K=2, che per una distribuzione normale porta ad un livello di confidenza approssimativamente del 95%.

The expanded uncertainty given by the Laboratory at the time of the phenomena of combustion is equal to 3,2 s. The probability that the criteria represent the truth observation is equal to 90%. The expanded uncertainty is calculated by multiplying the combined standard uncertainty for a coverage factor k = 2, which for a normal distribution leads to a confidence level of approximately 95%.

**Il Responsabile Laboratorio
The Laboratory Manager**

Fausto Albonico