

Report date:





Centro Tessile Serico Spa consortile

Via Castelnuovo, 3 - 22100 Como, Italia Tel. +39 031 331211-120 Fax +39 031 3312180 Amministrazione/Contabilità Tel. +39 0313312102-154 P IVA - C F 02381270137 Capitale sociale euro 552.693.18 i.v. mailbox@textilecomo.com www.textilecomo.com



MARIO SIRTORI SPA

Fax.nr. +39 031 855397



LAB nº 0045

TEST REPORT

Report nr.: 1803618-001 Customer code: 5485

26-lug-18

via Papa Giovanni XXIII 10 Acceptance code: 1803618 23845 COSTA MASNAGA (LC) Acceptance date: 28-giu-18

Italia Start test date: 28-giu-18

To the attention of: End test date: 26-lug-18 sig. Sergio Sala Crist

References: Tel.nr: +39 031 879632

Sampling by customer

EVEREST Article description:

Declared composition: 75% WOOL - 15% ALPACA - 10% POLYAMIDE

End use: **Furnishing** Typology: **Fabric**

Return: Specimens enclosed

The results reported herein refer to the tested samples only and do not involve any product approval by Centro Tessile Serico. This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory.

M.U.

TEST RESULTS

14063-ABRASION RESISTANCE (Martindale method): SPECIMENS BREAKDOWN

UNI EN ISO 12947-2:2017 Method: Instrument: Abrasion Tester Martindale

SPECIMEN BREAKDOWN (END POINT):

The breakdown point of the specimen is reached when:

- -Woven fabric (without pile): Two threads completely broken
- -Knitted fabric (without pile): One thread completely broken
- -Cut pile woven fabric: Two threads completely broken
- -Cut pile knitted fabric: One thread completely broken
- -Woven pile fabric with chenille yarns: Two threads completely broken
- -Knitted pile fabric with chenille yarns: One thread completely broken
- -Woven uncut pile fabric: Two threads completely broken
- -Knitted uncut pile fabric: One thread completely broken
- -Woven raised fabric: Two threads completely broken
- -Knitted raised fabric: One thread completely broken
- -Flocked fabrics: tested area completely worn off
- -Non-woven fabrics: surface layer shows a worn of diameter 2,5 mm

03-07-2018 Date of test:

No one Pretreatment carried out 130000 First specimen: cycles to end point cycles 170000 Second specimen: cycles to end point cycles >200000 Third specimen: cycles to end point cycles 130000 QUOTED RESULT: the lowest individual value cycles

Change of appearance: pilling formation is observed.

Pagina 1\2

^{(*) =} the tests marked with asterisk are not accredited by Accredia.







Centro Tessile Serico Spa consortile Via Castelnuovo, 3 - 22100 Como, Italia

Via Castelnuovo, 3 - 22100 Como, Italia
Tel. +39 031 331211-120 Fax +39 031 3312180
Amministrazione/Contabilità
Tel. +39 0313312102-154
P.IVA - C.F. 02381270137
Capitale sociale euro 552.693,18 i.v.
mailbox@textilecomo.com
www.textilecomo.com





LAB n° 0045

Report nr. 1803618-001

TEST	M.U.	RESULTS	
Load applied	kPa	12	
Change in colour	grade	Not requested	
Deviation from procedure		-	
Enclosed:	nr.	1	

END OF TEST REPORT

Technical Head

Enrica Baldini