

Centro Tessile Serico Sostenibile Srl

mailbox@textilecomo.com www.textilecomo.com

via Castelnuovo, 3 - 22100 Como Italia Pho +39 031 3312111/120 Fax: +39 0313312149 Amministrazione/Contabilità +39 031 3312102-154 P. IVA - C.F. 003900470133 Capitale sociale euro 600000,00 iv



Customer Code 05485

MARIO SIRTORI SPA

Phone: +39 031 879632

via Papa Giovanni XXIII 10

23845 COSTA MASNAGA (LC) Italia

sig. Sergio Sala Crist

Dear:



LAB N° 0045 L

Test Report No.: **2201096-001**

Date Test Report 14-feb-22

Acceptance: **2201096**

Arrival date sample 11-feb-22
Start date test 11-feb-22

End date test 14-feb-22

References:

[C] Item:

Sampling Mode: Sampling by Customer *

ANNIK

[C] Declared Compostion: 44% RWO - 28% WO - 16% PA - 6% WP - 3% RAF - 3% RPA

 [C] End use:
 furnishing

 [C] Typology:
 fabric

 Return:
 no requested

Test Results

Test	Method	U.M.	Result
15066 UPHOLSTERY FURNITURE COMPONENTS: ASSESSMENT OF THE IGNITABILITY BY SMOULDERING CIGARE	NFPA 260:2019 (except Par 4.2, 6.5, 7.6)		
Test carried out on			COVER FABRIC
Pretreatment carried out			none
Ignition source			SMOULDERING CIGARETTE
Materials of test assembly			
Upholstery filling: NON fire retardant pol Inner cover: - Outer cover: SEE ARTICLE DESCRIPTION	lyurethane foam with a density of 28 kg/m³		
TEST RESULT			CLASS 1
Deviations from the method			none
Annex n.			1F
Details of the test results related to each speci	men can be seen in the annex of this test report.		

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the Sample as received and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

 $This \ Report \ may \ not \ be \ reproduced \ in \ part, \ unless \ written \ permission \ of \ Centro \ Tessile \ Serico \ Sostenibile \ Srl \ Laboratory.$

[[]C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



Centro Tessile Serico Sostenibile Srl

Capitale sociale euro 600000,00 iv

mailbox@textilecomo.com

via Castelnuovo, 3 - 22100 Como Italia Pho +39 031 3312111/120 Fax: +39 0313312149 Amministrazione/Contabilità +39 031 3312102-154 P. IVA - C.F. 003900470133





LAB N° 0045 L

Test Report No.:	2201096-001		
Test	Method	U.M.	Result
			The Laboratory Manager Fausto Albonico
	END OF	REPORT	

The Results contained in this Report refer only to the Sample as received and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

^{(*) =} The tests marked in this way are not accredited by Accredia

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



Centro Tessile Serico Sostenibile Srl

Via Castelnuovo, 3 – 22100 Como Italia Tel. +39 031331211 Fax +39 0313312149 Amministrazione/Contabilità +39 0313312102-154 P.IVA – C.F. 03900470133

Capitale sociale euro 600.000,00 iv mailbox@textilecomo.com

www.textilecomo.com





I AR Nº 0045 I

Annex n. 1F to test report n. 2201096-001

DETAILS OF TEST RESULTS

Test executed according to NPFA 260:2019
Standard Methods of Tests and Classification System for Cigarette Ignition Resistance of Components of Upholstered Furniture

Sample description: ANNIK

Declared composition: 44% RWO - 28% WO - 16% PA - 6% WP - 3% RAF - 3% RPA

Conditioning of test specimen and ignition source: 21 ± 2.8 °C, <65% r.h.

Testing temperature and r.h.: 17°C, 45% r.h.

Filling specification: NON FIRE-RETARDANT polyurethane foam with a density of 28 kg/m³

Date of test: 14.02.2022

Specimen number		2	3
Total combustion of the cigarette (YES / NO)		NO	NO
Time of progressive smouldering from placement of the source (min)		25	25
Size of the damage in the vertical direction (mm)		11	11
Obvious ignition occurs (YES / NO)		NO	NO
CIGARETTE TEST RESULT (Class I/Class II)		Class I	Class I

Cover Fabric Classification (ref. NFPA 260:2019)

CLASS I

When subjected to the cover fabric test, a specimen shall show no evidence of ignition of any test assembly. The vertical char on any of the three specimens shall not exceed 45 mm.

CLASS II

Cover fabrics that do not meet Class I criteria shall be designated as Class II.

The following test result relate only to the ignitability of the combination of materials under the particolar conditions of test. They are not intended as a means of assessing the full potential fire hazard of the material in use.

The probability that the criteria represent the truth observation is equal to 95%.

The expanded uncertainty is calculated by multiplying the combined standard uncertainty for a coverage factor k = 2, which for a normal distribution leads to a confidence level of approximately 95%.

The Laboratory Manager Falisto Albertion