

TEST REPORT

Report nr.: **2000468-006**

Report date: **05-feb-20**

Acceptance code: **2000468**

Acceptance date: **23-gen-20**

Start test date: **23-gen-20**

End test date: **05-feb-20**

References: ---

Customer code: 5485

To:
MARIO SIRTORI SPA
via Papa Giovanni XXIII 10
23845 COSTA MASNAGA (LC)
Italia

To the attention of:

sig. Sergio Sala Crist

Tel.nr: +39 031 879632

Fax.nr.: +39 031 855397

Sampling by customer

Article description:

Declared composition:

End use:

Typology:

Return:

DARWIN

58% Viscose - 31% Cotton - 11% Flax

Furnishing

Fabric

Specimens enclosed

The results reported herein refer exclusively to the tested sample as received and do not involve any product approval by Centro Tessile Serico. This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory. The informations as Article Description, Declared Composition and Tipology listed above are data supplied by the Customer for which this Laboratory declines any responsibility.

TEST	M.U.	RESULTS
25145 DIMENSIONAL CHANGE TO DRYCLEANING WITH PERCHLOROETHYLENE		
Method:	UNI EN ISO 3759:2011 + UNI EN ISO 3175-1-2:2018 + UNI EN ISO 5077:2008	
Instrument:	Dry cleaning machine with Perchloroethylene	
Solvent used: PERCHLOROETHYLENE		
Dry cleaning procedure: Sensible		
Finishing: Type B - pressing by ironing with steam at 2 points (150°C)		
No.of dry cleaning and finishing treatments: 01		
No.of specimens for each tests: 01		
Dimensional changes after dry-cleaning (without finishing)		
DIMENSIONAL CHANGE - WIDTH direction	%	-0,6
DIMENSIONAL CHANGE - LENGTH direction	%	-1,6
Dimensional changes after dry-cleaning and finishing		
DIMENSIONAL CHANGE - WIDTH direction	%	0,0
DIMENSIONAL CHANGE - LENGTH direction	%	-2,5

(*) = the tests marked with asterisk are not accredited by Accredia.

Report nr.

2000468-006

TEST

M.U.

RESULTS

----- **END OF TEST REPORT** -----

Technical Head

Enrica Baldini

