

TEST REPORT

Report nr.: **2001032-001**

Report date: **19-feb-20**

Acceptance code: **2001032**

Acceptance date: **12-feb-20**

Start test date: **12-feb-20**

End test date: **19-feb-20**

References: ---

Customer code: 5485

To:
MARIO SIRTORI SPA
via Papa Giovanni XXIII 10
23845 COSTA MASNAGA (LC)
Italia

To the attention of:

sig. Sergio Sala Crist

Tel.nr: +39 031 879632

Fax.nr.: +39 031 855397

Sampling by customer

Article description:

Declared composition:

End use:

Typology:

Return:

DARWIN

58% Viscose - 31% Cotton - 11% Flax

Furnishing

Fabric

No requested

The results reported herein refer exclusively to the tested sample as received and do not involve any product approval by Centro Tessile Serico. This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory. The informations as Article Description, Declared Composition and Tipology listed above are data supplied by the Customer for which this Laboratory declines any responsibility.

TEST	M.U.	RESULTS
14253 TEAR PROPERTIES OF FABRICS WING SHAPED (2 directions)		
Method:	UNI EN ISO 13937-3/02	
Instrument:	CRE Dynamometer	
Date of test:		18-02-2020
Tear force of yarns WARP - Average	N	104
Tear force of yarns WEFT - Average	N	198
Number of specimens for each direction	n.	3
Number of specimens rejected:	nr.	0
Deviation from procedure		.
Because of the fabric lack, the test was carried out on n. 3 specimens instead of n.5, as previewed by the standard method, this deviation can influence the test result.		

(*) = the tests marked with asterisk are not accredited by Accredia.

Report nr.

2001032-001

TEST

M.U.

RESULTS

----- **END OF TEST REPORT** -----

Technical Head

Enrica Baldini

