



REPORT

Report nr.: **1500865-001**
Report date: **05-feb-15**
Acceptance code: **1500865**
Acceptance date: **04-feb-15**
Start test date: **04-feb-15**
End test date: **05-feb-15**
References: ---

Customer code: 5485

To:
MARIO SIRTORI SPA
via Papa Giovanni XXIII 10
23845 COSTA MASNAGA (LC)
Italia

To the attention of:
sig.ra Francesca Agliati
Tel.nr: +39 031 879632
Fax.nr.: +39 031 855397

Article description: **SOLE**
Declared composition: **100% Trevira**
End use: **Furnishing**
Return: **No requested**
Sampling by customer

The results reported herein refer to the tested samples only and do not involve any product approval by Centro Tessile Serico.
This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory.

TEST	M.U.	RESULTS
15066 UPHOLSTERY FURNITURE: assessment of the ignitability by SMOULDERING CIGARETTE		
Method:	TB 117: 2013	
Instrument:	Mock-up Tester	
Test executed on:		COVER FABRIC
Ignition source applied:		
source 0 (SMOULDERING CIGARETTE)		
Materials of test assembly:		
Upholstery filling: NON fire retardant polyurethane foam with a density of 28 kg/m ³		
Inner cover: -		
Outer cover: SEE ARTICLE DESCRIPTION		
TEST RESULT:		SAMPLE PASSES THE TEST
Note: to assess the ignitability of this sample, the test has been carried out using a NON fire-retardant polyurethane foam with a density of 28 kg/m ³ as filling of the upholstered seating. The test result could be different using another type of filling material.		
Annex n.:		1F
Details of the test results related to each specimen can be seen in the annex of this test report.		

Centro Tessile Serico



Centro Tessile Serico Spa consortile
via Castelnuovo, 3 22100 Como, Italia
P.IVA - C.F. 02381270137
Capitale sociale 541.666,78 i.v.
mailto:mailbox@textilecomo.com
www.textilecomo.com

Servizio Clienti Laboratorio +39 031 3312120
Segreteria Laboratorio +39 031 3312121-170-171
Segreteria di Direzione
e Amministrazione +39 031 3312102
Contabilità +39 031 3312154
Area Certificazione +39 031 3312133
Marchio Seri.co +39 031 3312132
Fax +39 031 3312180

Report nr.

1500865-001

TEST

M.U.

RESULTS

END OF REPORT

Supervisor Head

Dr. Giovanna Baglio

Technical Head

Prof. Mario Frigerio



Annex n. 1F to test report n. 1500865-001

DETAILS OF TEST RESULTS

**Test executed according to TB 117:2013
Requirements, Test procedure and Apparatus for testing the Smolder Resistance of
Materials used in Upholstered Furniture**

Sample description: **SOLE**

Declared composition: **100% Trevira**

Conditioning of test specimen and ignition source: **24 h at 21 ± 3 °C, <55% r.h.**

Testing temperature and r.h.: **18°C, 40% r.h.**

Filling specification: **NON FIRE-RETARDANT polyurethane foam with a density of 28 kg/m³**

Date of test: **05.02.2015**

Type of fabric: COVER FABRIC

Specimen number	1	2	3
Total combustion of the cigarette (YES / NO)	YES	YES	YES
Time of progressive smouldering from placement of the source (min)	32	30	30
Combustion of the sample (YES / NO)	YES	YES	YES
Size of the damage in the vertical direction (mm)	28	24	26
Combustion observed in polyurethane backing (YES / NO)	YES	YES	YES
CIGARETTE TEST RESULT (PASS/FAIL)	PASS	PASS	PASS

Cover Fabric Classification (ref. TB 117:2013)

A single mock-up test specimen fails to meet the requirements if any of the following criteria occurs:

- a) The mock-up test specimen continues to smolder after the 45 minute test duration;
- b) A vertical char length of more than 45 mm develops on the cover fabric
- c) The mock-up test specimen transitions to open flaming.

2. The cover fabric passes the test if three initial mock-up specimens pass the test, i.e., the cigarettes burn their full length and the mock-ups are no longer smoldering.

3. If more than one initial specimen fails, the cover fabric fails the test.

4. If any one of the three initial specimens fails, repeat the test on additional three specimens.

5. If all three additional specimens pass the test, the cover fabric passes the test. If any one of the additional three specimens fails, the cover fabric fails the test.

The following test result relate only to the ignitability of the combination of materials under the particular conditions of test.

They are not intended as a means of assessing the full potential fire hazard of the material in use.