

TEST REPORT

Report nr.: **2000720-001**

Report date: **13-feb-20**

Acceptance code: **2000720**

Acceptance date: **04-feb-20**

Start test date: **04-feb-20**

End test date: **12-feb-20**

References: **---**

Customer code: 5485

To:
MARIO SIRTORI SPA
via Papa Giovanni XXIII 10
23845 COSTA MASNAGA (LC)
Italia

To the attention of:

sig.ra Laura Misseri

Tel.nr: +39 031 879632

Fax.nr.: +39 031 855397

Sampling by customer

Article description:

Declared composition:

End use:

Typology:

Return:

MARSHMALLOW

100% Polyester

Furnishing

Fabric

No requested

The results reported herein refer exclusively to the tested sample as received and do not involve any product approval by Centro Tessile Serico. This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory. The informations as Article Description, Declared Composition and Tipology listed above are data supplied by the Customer for which this Laboratory declines any responsibility.

| TEST | M.U. | RESULTS |
|---|------|------------|
| 1443 SLIPPAGE RESISTANCE OF YARNS AT A SEAM - fixed load | | - |
| Method: UNI EN ISO 13936-2/2004 | | |
| Instrument: CRE Dynamometer | | |
| FURNISHING: | | |
| Sewing thread : 100% polyester, Linear density 74 tex | | |
| Plain lockstitch type n.301 (ISO 4915:1991) | | |
| Needle: number metric 110 | | |
| Stitches/100 mm: 32 ± 2 | | |
| Date of test: | | 12/02/2020 |
| Force applied | N | 180 |
| WARP over WEFT - seam opening | mm | 2,0 |
| WEFT over WARP - seam opening | mm | 2,0 |
| Number of specimens for each direction | n. | 5 |
| Statement occurred: | | - |

(*) = the tests marked with asterisk are not accredited by Accredia.

Report nr.

2000720-001

TEST

M.U.

RESULTS

----- **END OF TEST REPORT** -----

Technical Head

Enrica Baldini

