



REPORT

Report nr.: **1600466-001**
Report date: **29-gen-16**
Acceptance code: **1600466**
Acceptance date: **22-gen-16**
Start test date: **22-gen-16**
End test date: **29-gen-16**
References: **---**

Customer code: 5485

To:
MARIO SIRTORI SPA
via Papa Giovanni XXIII 10
23845 COSTA MASNAGA (LC)
Italia

To the attention of:
sig. Sergio Sala Crist

Tel.nr: +39 031 879632

Fax.nr.: +39 031 855397

Article description: **VELL LARIO**
Declared composition: **100% Cotton**
End use: **Furnishing**
Typology: **Fabric**
Return: **No requested**
Sampling by customer

The results reported herein refer to the tested samples only and do not involve any product approval by Centro Tessile Serico.
This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory.

| TEST | M.U. | RESULTS |
|--|-------------------------|------------|
| 14443 SLIPPAGE RESISTANCE OF YARNS AT A SEAM - fixed load | | |
| Method: | UNI EN ISO 13936-2/2004 | |
| Instrument: | CRE Dynamometer | |
| FURNISHING: | | |
| Sewing thread : 100% polyester, Title 74 tex | | |
| Plain lockstitch type n.301 (ISO 4915:1991) | | |
| Needle: number metric 110 | | |
| Stitches/100 mm: 32 ± 2 | | |
| Date of test: | | 29/01/2016 |
| Force applied | N | 180 |
| WARP over WEFT - seam opening | mm | 2,0 |
| WEFT over WARP - seam opening | mm | 1,7 |
| Statement occurred: | | - |

END OF REPORT

Supervisor Head

p.i. Giovanna Baglio

Technical Head

dott. Marco Piu