



## REPORT

Report nr.: **1501655-002**

Report date: **17-mar-15**

Acceptance code: **1501655**

Acceptance date: **04-mar-15**

Start test date: **04-mar-15**

End test date: **17-mar-15**

References: **---**

Customer code: **5485**

To:  
**MARIO SIRTORI SPA**  
**via Papa Giovanni XXIII 10**  
**23845 COSTA MASNAGA (LC)**  
**Italia**

To the attention of:  
**sig.ra Francesca Agliati**

Tel.nr: **+39 031 879632**

Fax.nr.: **+39 031 855397**

Article description: **ROXANA 01 CS**  
Declared composition: **100% Trevira**  
End use: **Furnishing**  
Typology: **Fabric**  
Return: **Sample enclosed**  
Sampling by customer

The results reported herein refer to the tested samples only and do not involve any product approval by Centro Tessile Serico.  
This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory.

TEST	M.U.	RESULTS
------	------	---------

**14443 SLIPPAGE RESISTANCE OF YARNS AT A SEAM - fixed load**

Method: UNI EN ISO 13936-2/2004

Instrument: CRE Dynamometer

**FURNISHING:**

Sewing thread : 100% polyester, Title 74 tex

Plain lockstitch type n.301 (ISO 4915:1991)

Needle: number metric 110

Stitches/100 mm: 32 ± 2

Date of test:

11/3/2015

Force applied

N

180

WARP over WEFT - seam opening

mm

1,8

WEFT over WARP - seam opening

mm

3,0

Number of specimens for each direction

n.

5

Statement occurred:



Report nr.

**1501655-002**

**TEST**

**M.U.**

**RESULTS**

**14253 TEAR PROPERTIES OF FABRICS WING SHAPED (2 directions)**

**Method:** UNI EN ISO 13937-3:2002+EC 1-2004

**Instrument:** CRE Dynamometer

Date of test:

11/3/2015

Tear force of yarns WARP - Average

44,0

Tear force of yarns WEFT - Average

28,2

Number of specimens for each direction

n.

5

Number of specimens rejected:

nr.

0

Deviation from procedure

-

**14203 TENSILE STRENGTH - strip method**

**Method:** UNI EN ISO 13934-1:2013

**Instrument:** CRE Dynamometer

Date of test:

11/3/2015

Gauge length

mm

200

Elongation speed used

mm/min

100

Pretension applied

N

10

Specimens condition

Conditioned

Number of specimens for each direction

n.

5

WARP - maximum force - average

N

1070

WARP - elongation to max. force - average

%

21,5

WEFT - maximum force - average

N

1183

WEFT - elongation to max. force - average

%

25,5

Number of specimens rejected:

nr.

0

Deviation from procedure

-