



REPORT

Report nr.: **1508146-001**
Report date: **02-dic-15**
Acceptance code: **1508146**
Acceptance date: **26-nov-15**
Start test date: **26-nov-15**
End test date: **02-dic-15**
References: ---

Customer code: 5485

To:
MARIO SIRTORI SPA
via Papa Giovanni XXIII 10
23845 COSTA MASNAGA (LC)
Italia

To the attention of:
sig. Sergio Sala Crist

Tel.nr: +39 031 879632
Fax.nr.: +39 031 855397

Article description: **ROXANA CS 01**
Declared composition: **100% Trevira**
End use: **Furnishing**
Typology: **Fabric**
Return: **No requested**
Sampling by customer

The results reported herein refer to the tested samples only and do not involve any product approval by Centro Tessile Serico.
This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory.

TEST

M.U.

RESULTS

15066 UPHOLSTERY FURNITURE: assessment of the ignitability by SMOULDERING CIGARETTE

Method: TB 117: 2013

Instrument: Mock-up Tester

Test executed on:

COVER FABRIC

Ignition source applied:

SMOULDERING CIGARETTE

Materials of test assembly:

Upholstery filling: NON fire retardant polyurethane foam with a density of 28 kg/m³

Inner cover: -

Outer cover: SEE ARTICLE DESCRIPTION

TEST RESULT:

SAMPLE PASSES THE TEST

Note: to assess the ignitability of this sample, the test has been carried out using a NON fire-retardant polyurethane foam with a density of 28 kg/m³ as filling of the upholstered seating.
The test result could be different using another type of filling material.

Annex n.:

1F

Details of the test results related to each specimen can be seen in the annex of this test report.



Annex n. 1F to test report n. 1508146-001

DETAILS OF TEST RESULTS

Test executed according to TB 117:2013

Requirements, Test procedure and Apparatus for testing the Smolder Resistance of Materials used in Upholstered Furniture

Sample description: **ROXANA CS 01**

Declared composition: **100% Trevira**

Conditioning of test specimen and ignition source: **24 h at 21 ± 3 °C, <55% r.h.**

Testing temperature and r.h.: **20 °C, 58% r.h.**

Filling specification: **NON FIRE-RETARDANT polyurethane foam with a density of 28 kg/m³**

Date of test: **30.11.2015**

Type of fabric: COVER FABRIC

Specimen number	1	2	3
Total combustion of the cigarette (YES / NO)	YES	YES	YES
Time of progressive smouldering from placement of the source (min)	32	31	31
Combustion of the sample (YES / NO)	YES	YES	YES
Size of the damage in the vertical direction (mm)	24	23	24
Combustion observed in polyurethane backing (YES / NO)	YES	YES	YES
CIGARETTE TEST RESULT (PASS/FAIL)	PASSES	PASSES	PASSES

Cover Fabric Classification (ref. TB 117:2013)

A single mock-up test specimen fails to meet the requirements if any of the following criteria occurs:

- The mock-up test specimen continues to smolder after the 45 minute test duration;
- A vertical char length of more than 45 mm develops on the cover fabric
- The mock-up test specimen transitions to open flaming.

2. The cover fabric passes the test if three initial mock-up specimens pass the test, i.e., the cigarettes burn their full length and the mock-ups are no longer smoldering.

3. If more than one initial specimen fails, the cover fabric fails the test.

4. If any one of the three initial specimens fails, repeat the test on additional three specimens.

5. If all three additional specimens pass the test, the cover fabric passes the test. If any one of the additional three specimens fails, the cover fabric fails the test.

The following test result relate only to the ignitability of the combination of materials under the particular conditions of test.

They are not intended as a means of assessing the full potential fire hazard of the material in use.