

TEST REPORT

Report nr.: **1804988-003**

Report date: **25-set-18**

Acceptance code: **1804988**

Acceptance date: **20-set-18**

Start test date: **20-set-18**

End test date: **25-set-18**

References: **---**

Customer code: 5485

To:
MARIO SIRTORI SPA
via Papa Giovanni XXIII 10
23845 COSTA MASNAGA (LC)
Italia

To the attention of:

sig. Sergio Sala Crist

Tel.nr: +39 031 879632

Fax.nr. +39 031 855397

Sampling by customer

Article description:

Declared composition:

End use:

Typology:

Return:

EVEREST

75% WO - 15% WP - 10% PA

Furnishing

Fabric

No requested

The results reported herein refer to the tested samples only and do not involve any product approval by Centro Tessile Serico.
This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory.

TEST	M.U.	RESULTS
14203 TENSILE STRENGTH - MAXIMUM FORCE AND ELONGATION AT MAXIMUM FORCE USING THE STRIP METHOD		
Method:	UNI EN ISO 13934-1:2013	
Instrument:	CRE Dynamometer	
Date of test:		25/09/2018
Gauge length	mm	200
Elongation speed used	mm/min	100
Pretension applied	N	10
Specimens condition		Conditioned
Number of specimens for each direction	n.	5
WARP - maximum force - average	N	769
WARP - elongation to max. force - average	%	25,0
WEFT - maximum force - average	N	937
WEFT - elongation to max. force - average	%	31,5
Number of specimens rejected:	nr.	0
Deviation from procedure		-

(*) = the tests marked with asterisk are not accredited by Accredia.



Centro Tessile Serico Spa consortile
Via Castelnuovo, 3 - 22100 Como, Italia
Tel. +39 031 331211-120 Fax +39 031 3312180
Amministrazione/Contabilità
Tel. +39 0313312102-154
P.IVA - C.F. 02381270137
Capitale sociale euro 552.693,18 i.v.
mailbox@textilecomo.com
www.textilecomo.com



LAB n° 0045

Report nr.

1804988-003

TEST

M.U.

RESULTS

----- **END OF TEST REPORT** -----

Technical Head

Enrica Baldini

(*) = the tests marked with asterisk are not accredited by Accredia.