

TEST REPORT

Report nr.: **1804988-002**

Report date: **25-set-18**

Acceptance code: **1804988**

Acceptance date: **20-set-18**

Start test date: **20-set-18**

End test date: **25-set-18**

References: **---**

Customer code: 5485

To:
MARIO SIRTORI SPA
via Papa Giovanni XXIII 10
23845 COSTA MASNAGA (LC)
Italia

To the attention of:

sig. Sergio Sala Crist

Tel.nr: +39 031 879632

Fax.nr. +39 031 855397

Sampling by customer

Article description:

EVEREST

Declared composition:

75% WO - 15% WP - 10% PA

End use:

Furnishing

Typology:

Fabric

Return:

No requested

The results reported herein refer to the tested samples only and do not involve any product approval by Centro Tessile Serico.
This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory.

TEST	M.U.	RESULTS
14253 TEAR PROPERTIES OF FABRICS WING SHAPED (2 directions)		
Method:	UNI EN ISO 13937-3:2002+EC 1-2004	
Instrument:	CRE Dynamometer	
Date of test:		24/09/2018
Tear force of yarns WARP - Average	N	114
Tear force of yarns WEFT - Average	N	121
Number of specimens for each direction	n.	5
Number of specimens rejected:	nr.	0
Deviation from procedure		-

END OF TEST REPORT

Technical Head

Enrica Baldini



(*) = the tests marked with asterisk are not accredited by Accredia.