

Test Report No.:	2203437-003	
Date Test Report	11-mag-22	Customer Code 05485
Acceptance:	2203437	Dear:
Arrival date sample	05-mag-22	MARIO SIRTORI SPA
Start date test	05-mag-22	via Papa Giovanni XXIII 10
End date test	11-mag-22	23845 COSTA MASNAGA (LC) Italia
References:		C.a. sig. Sergio Sala Crist
		Phone: +39 031 879632
Sampling Mode:	Campionamento effettuato dal Committente *	
[C] Item:	SERIE MONTREAL	
[C] Declared Composition:	65% WV - 24% CO - 6% AF - 5% PL	
[C] End use:	furnishing	
[C] Typology:	fabric	
Return:	no requested	

Test Results

Test	Method	U.M.	Result
15066 UPHOLSTERY FURNITURE COMPONENTS: ASSESSMENT OF THE IGNITABILITY BY SMOULDERING CIGARETTE		NFPA 260:2019 (except Par 4.2, 6.5, 7.6)	.
Start date test	11/05/2022		
End date test	11/05/2022		
Instrument: Small Test Rig and burner			
Test carried out on			COVER FABRIC
Ignition source			SMOULDERING CIGARETTE
Materials of test assembly			.
Upholstery filling: NON fire retardant polyurethane foam with a density of 28 kg/m³			
Inner cover: -			
Outer cover: SEE ARTICLE DESCRIPTION			
TEST RESULT			CLASS 1
Deviations from the method			none
Annex n.			1F
Details of the test results related to each specimen can be seen in the annex of this test report.			

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the Sample as received and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



Centro Tessile Serico Sostenibile Srl
via Castelnuovo, 3 - 22100 Como Italia
Pho +39 031 3312111/120 Fax: +39 0313312149
Amministrazione/Contabilità +39 031 3312102-154
P. IVA - C.F. 003900470133
Capitale sociale euro 600000,00 iv
mailbox@textilecomo.com



LAB N° 0045 L

Test Report No.: **2203437-003**

Test	Method	U.M.	Result
------	--------	------	--------

The Laboratory Manager

Fausto Albonico

END OF REPORT

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the Sample as received and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



Centro Tessile Serico Sostenibile Srl
Via Castelnuovo, 3 – 22100 Como Italia
Tel. +39 031331211 Fax +39 0313312149
Amministrazione/Contabilità +39 0313312102-154
P.IVA – C.F. 03900470133
Capitale sociale euro 600.000,00 iv
mailbox@textilecomo.com
www.textilecomo.com



LAB N° 0045 L

Annex n. 1F to test report n. 2203437-003

DETAILS OF TEST RESULTS

Test executed according to NFPA 260:2019

Standard Methods of Tests and Classification System for Cigarette Ignition Resistance of Components of Upholstered Furniture

Sample description: **SERIE MONTREAL**

Declared composition: **65% WV - 24% CO - 6% AF - 5% PL**

Conditioning of test specimen and ignition source: **21 ± 2,8 °C, <65% r.h.**

Testing temperature and r.h.: **19°C, 67% r.h.**

Filling specification: **NON FIRE-RETARDANT polyurethane foam with a density of 28 kg/m³**

Date of test: **11/05/2022**

Specimen number	1	2	3
Total combustion of the cigarette (YES / NO)	YES	YES	YES
Time of progressive smouldering from placement of the source (min)	34	33	36
Size of the damage in the vertical direction (mm)	20	18	21
Obvious ignition occurs (YES / NO)	NO	NO	NO
CIGARETTE TEST RESULT (Class I/Class II)	Class I	Class I	Class I

Cover Fabric Classification (ref. NFPA 260:2019)

CLASS I

When subjected to the cover fabric test, a specimen shall show no evidence of ignition of any test assembly. The vertical char on any of the three specimens shall not exceed 45 mm.

CLASS II

Cover fabrics that do not meet Class I criteria shall be designated as Class II.

The following test result relate only to the ignitability of the combination of materials under the particular conditions of test. They are not intended as a means of assessing the full potential fire hazard of the material in use.

The probability that the criteria represent the truth observation is equal to 95%.

The Laboratory Manager
Fausto Albani