



## REPORT

Report nr.: **1600357-001**  
Report date: **29-gen-16**  
Acceptance code: **1600357**  
Acceptance date: **21-gen-16**  
Start test date: **21-gen-16**  
End test date: **29-gen-16**  
References: **---**

Customer code: 5485

**To:**  
**MARIO SIRTORI SPA**  
**via Papa Giovanni XXIII 10**  
**23845 COSTA MASNAGA (LC)**  
**Italia**

To the attention of:  
sig. Sergio Sala Crist

Tel.nr: +39 031 879632

Fax.nr.: +39 031 855397

Article description: **TUNDRA 01**  
Declared composition: **42% Viscose - 36% Cotton - 16% Acrylic - 6% Polyester**  
End use: **Furnishing**  
Typology: **Fabric**  
Return: **No requested**  
Sampling by customer

The results reported herein refer to the tested samples only and do not involve any product approval by Centro Tessile Serico.  
This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory.

TEST	M.U.	RESULTS
<b>14443 SLIPPAGE RESISTANCE OF YARNS AT A SEAM - fixed load</b>		
<b>Method:</b> UNI EN ISO 13936-2/2004		
<b>Instrument:</b> CRE Dynamometer		
<b>FURNISHING:</b>		
Sewing thread : 100% polyester, Title 74 tex		
Plain lockstitch type n.301 (ISO 4915:1991)		
Needle: number metric 110		
Stitches/100 mm: 32 ± 2		
Date of test:		29/01/2016
Force applied	N	180
WARP over WEFT - seam opening	mm	1,0
WEFT over WARP - seam opening	mm	1,3
Statement occurred:		-

END OF REPORT

**Supervisor Head**

p.i. Giovanna Baglio

**Technical Head**

dott. Marco Piu