



REPORT

Report nr.: **1600358-001**
Report date: **29-gen-16**
Acceptance code: **1600358**
Acceptance date: **21-gen-16**
Start test date: **21-gen-16**
End test date: **29-gen-16**
References: **---**

Customer code: 5485

To:
MARIO SIRTORI SPA
via Papa Giovanni XXIII 10
23845 COSTA MASNAGA (LC)
Italia

To the attention of:
sig. Sergio Sala Crist

Tel.nr: +39 031 879632

Fax.nr.: +39 031 855397

Article description: **TUNDRA 01**
Declared composition: **42% Viscose - 36% Cotton - 16% Acrylic - 6% Polyester**
End use: **Furnishing**
Typology: **Fabric**
Return: **No requested**
Sampling by customer

The results reported herein refer to the tested samples only and do not involve any product approval by Centro Tessile Serico.
This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory.

TEST	M.U.	RESULTS
14253 TEAR PROPERTIES OF FABRICS WING SHAPED (2 directions)		
Method:	UNI EN ISO 13937-3:2002+EC 1-2004	
Instrument:	CRE Dynamometer	
Date of test:		29/01/2016
Tear force of yarns WARP - Average		477 N
Mean of the maximum peaks. The resistance of the threads in this direction doesn't permit the tear of the fabric.		
Tear force of yarns WEFT - Average		413 N
Mean of the maximum peaks. The resistance of the threads in this direction doesn't permit the tear of the fabric.		
Deviation from procedure		-

END OF REPORT

Supervisor Head

p.i. Giovanna Baglio

Technical Head

dott. Marco Piu