

TEST REPORT

Report nr.: **1802698-001**
Report date: **25-mag-18**
Acceptance code: **1802698**
Acceptance date: **16-mag-18**
Start test date: **16-mag-18**
End test date: **25-mag-18**
References: ---

Customer code: 5485

To:
MARIO SIRTORI SPA
via Papa Giovanni XXIII 10
23845 COSTA MASNAGA (LC)
Italia

To the attention of:
sig. Sergio Sala Crist

Tel.nr: +39 031 879632

Fax.nr.: +39 031 855397

Article description: **LINVIRA Cs**
Declared composition: **100% Trevira**
End use: **Furnishing**
Typology: **Fabric**
Return: **Specimens enclosed**
Sampling by customer

The results reported herein refer to the tested samples only and do not involve any product approval by Centro Tessile Serico.
This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory.

TEST	M.U.	RESULTS
20585 COLOUR FASTNESS TO ARTIFICIAL WEATHERING - Xenon arc fading lamp test		
Method:	UNI EN ISO 105 B04/00	
Instrument:	Q-SUN XE-2-HS	
Exposure method:	2	
Exposure conditions:		
-Light:	29 minutes	
-Light + water:	1 minute	
-Chamber temperature:	38°C	
Blue wool standard:	series from 1 to 8	
Assessment cabinet:	provide to ISO 105 A01, under D65 (Artificial Daylight) illumination	
Colour fastness to artificial weathering	grade	6-7

END OF TEST REPORT

Technical Head

Enrica Baldini

