

TEST REPORT

Report nr.: **1803145-001**

Report date: **22-giu-18**

Acceptance code: **1803145**

Acceptance date: **08-giu-18**

Start test date: **08-giu-18**

End test date: **22-giu-18**

References: **---**

Customer code: 5485

To:
MARIO SIRTORI SPA
via Papa Giovanni XXIII 10
23845 COSTA MASNAGA (LC)
Italia

To the attention of:

sig. Sergio Sala Crist

Tel.nr: +39 031 879632

Fax.nr. +39 031 855397

Sampling by customer

Article description:

Declared composition:

End use:

Typology:

Return:

LINVIRA CS
100% Trevira
Furnishing
Fabric
No requested

The results reported herein refer to the tested samples only and do not involve any product approval by Centro Tessile Serico.
This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory.

TEST	M.U.	RESULTS
14443 SLIPPAGE RESISTANCE OF YARNS AT A SEAM - fixed load		
Method:	UNI EN ISO 13936-2/2004	
Instrument:	CRE Dynamometer	
FURNISHING:		
Sewing thread : 100% polyester, Linear density 74 tex		
Plain lockstitch type n.301 (ISO 4915:1991)		
Needle: number metric 110		
Stitches/100 mm: 32 ± 2		
Date of test:		14/06/2018
Force applied	N	180
WARP over WEFT - seam opening	mm	3,0
WEFT over WARP - seam opening	mm	2,0
Number of specimens for each direction	n.	5
Statement occurred:		-

(*) = the tests marked with asterisk are not accredited by Accredia.



Centro Tessile Serico Spa consortile
Via Castelnuovo, 3 - 22100 Como, Italia
Tel. +39 031 331211-120 Fax +39 031 3312180
Amministrazione/Contabilità
Tel. +39 0313312102-154
P.IVA - C.F. 02381270137
Capitale sociale euro 552.693,18 i.v.
mailbox@textilecomo.com
www.textilecomo.com



LAB n° 0045

Report nr.

1803145-001

TEST

M.U.

RESULTS

----- **END OF TEST REPORT** -----

Technical Head

Enrica Baldini

(*) = the tests marked with asterisk are not accredited by Accredia.