

Centro Tessile Serico Sostenibile Srl

www.textilecomo.com

via Castelnuovo, 3 - 22100 Como Italia Pho +39 031 3312111/120 Fax: +39 0313312149 Amministrazione/Contabilità +39 031 3312102-154 P. IVA - C.F. 003900470133 Capitale sociale euro 600000,00 iv mailbox@textilecomo.com



Customer Code 05485

MARIO SIRTORI SPA

Phone: +39 031 879632

via Papa Giovanni XXIII 10

23845 COSTA MASNAGA (LC) Italia

sig. Sergio Sala Crist

Dear:

C.a.



LAB N° 0045 L

Test Report No.: 2100199-001

Date Test Report 20-gen-21

2100199 Acceptance:

Arrival date sample 11-gen-21 Start date test 11-gen-21

End date test 20-gen-21

References:

[C] Item:

Sampling Mode: Sampling by Customer *

CARNIVAL

[C] Declared Compostion: 40% Cotton - 22% Acrylic - 16% Viscose - 11% Wool - 11% Polyester

[C] End use: **Furnishing Fabric** [C] Typology:

Return: Specimens enclosed

Test Results

Test	Method	U.M.	Result
14063-ABRASION RESISTANCE (Martindale	UNI EN ISO 12947-2:2017		

method): SPECIMENS BREAKDOWN

Instrument: Abrasion Pillometer

SPECIMEN BREAKDOWN (END POINT):

- The breakdown point of the specimen is reached when:
- Woven fabric (without pile): Two threads completely broken; - Knitted fabric (without pile): One thread completely broken;
- Cut pile woven fabric: Two threads completely broken or fully worn of area;
- Cut pile knitted fabric: One thread completely broken or fully worn of area;
- Woven pile fabric with chenille yarns: Two threads completely broken or fully worn of area; - Knitted pile fabric with chenille yarns: One thread completely broken or fully worn of area;
- Woven uncut pile fabric: Two threads completely broken or fully worn of area;
- Knitted uncut pile fabric: One thread completely broken or fully worn of area;
- Woven raised fabric: Two threads completely broken;
- Knitted raised fabric: One thread completely broken;
- Flocked fabrics: tested area completely worn off;
- Non-woven fabrics: surface layer shows a worn of diameter 2,5 mm

- · · · · · ·		
Date of test		12/01/2021
Pretreatment carried out		NO ONE
First specimen: cycles to end point	cycles	100000
Second specimen: cycles to end point	cycles	100000
Third specimen: cycles to end point	cycles	100000
QUOTED RESULT: the lowest individual value	cycles	100000
Load applied	kpa	12
Change in appareance		

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the Sample as received and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



Centro Tessile Serico Sostenibile Srl

mailbox@textilecomo.com

via Castelnuovo, 3 - 22100 Como Italia Pho +39 031 3312111/120 Fax: +39 0313312149 Amministrazione/Contabilità +39 031 3312102-154 P. IVA - C.F. 003900470133 Capitale sociale euro 600000,00 iv





LAB N° 0045 L

Test Report No.: 2100199-001

Test	Method	u.m.	Result
Colour change at 6000 cycles		grade	
Deviation from procedure			
n. attachements		No.	1

The Laboratory Manager
Fausto Albonico

END OF REPORT

The Results contained in this Report refer only to the Sample as received and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl.

Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

^{(*) =} The tests marked in this way are not accredited by Accredia

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[[]C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.