



Centro Tessile Serico Spa consortile
Via Castelnuovo, 3 - 22100 Como, Italia
Tel. +39 031 331211-120 Fax +39 031 3312180
Amministrazione/Contabilità
Tel. +39 0313312102-154
P.IVA - C.F. 02381270137
Capitale sociale euro 552.693,18 i.v.
mailto:mailbox@textilecomo.com
www.textilecomo.com

TEST REPORT

Report nr.: **1704221-001**
Report date: **06-set-17**
Acceptance code: **1704221**
Acceptance date: **04-set-17**
Start test date: **04-set-17**
End test date: **06-set-17**
References: ---

Customer code: 5485

To:
MARIO SIRTORI SPA
via Papa Giovanni XXIII 10
23845 COSTA MASNAGA (LC)
Italia

To the attention of:
sig. Sergio Sala Crist
Tel.nr: +39 031 879632
Fax.nr.: +39 031 855397

Article description: **VELL. ALPACA**
Declared composition: **39% Cotton - 28% Alpaca - 11% Polyester - 9% Virgin Wool - 7% Polyamide - 6% Viscose**
End use: **Furnishing**
Typology: **Fabric**
Return: **No requested**
Sampling by customer

The results reported herein refer to the tested samples only and do not involve any product approval by Centro Tessile Serico.
This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory.

TEST	M.U.	RESULTS
15066 UPHOLSTERY FURNITURE: assessment of the ignitability by SMOULDERING CIGARETTE		
Method:	TB 117: 2013	
Instrument:	Mock-up Tester	
Test executed on:		COVER FABRIC
Ignition source applied:		*
SMOULDERING CIGARETTE		
Materials of test assembly:		*
Upholstery filling: NON fire retardant polyurethane foam with a density of 28 kg/m ³		
Inner cover: -		
Outer cover: SEE ARTICLE DESCRIPTION		
TEST RESULT:		SAMPLE PASSES THE TEST
Note: to assess the ignitability of this sample, the test has been carried out using a NON fire-retardant polyurethane foam with a density of 28 kg/m ³ as filling of the upholstered seating. The test result could be different using another type of filling material.		
Annex n.:		1F
Details of the test results related to each specimen can be seen in the annex of this test report.		



CTS

Centro Tessile Serico



CTS
Esa Systems

Centro Tessile Serico Spa consortile

Via Castelnuovo, 3 - 22100 Como, Italia
Tel. +39 031 331211-120 Fax +39 031 3312180
Amministrazione/Contabilità
Tel. +39 0313312102-154
P.IVA - C.F. 02381270137
Capitale sociale euro 552.693,18 i.v.
mailbox@textilecomo.com
www.textilecomo.com

Report nr.

1704221-001

TEST

M.U.

RESULTS

END OF TEST REPORT

Technical Head

Enrica Baldini



Centro Tessile Serico Spa consortile
Via Castelnuovo, 3 - 22100 Como, Italia
Tel +39 031 331211/120 Fax +39 031 3312180
Amministrazione/Contabilità +39 031 3312102-154
P.IVA - C.F. 02381270137
Capitale sociale euro 552.693,18 i.v.
mailbox@textilecomo.com
www.textilecomo.com

Annex n. 1F to test report n. 17042-001

DETAILS OF TEST RESULTS

Test executed according to TB 117:2013

Requirements, Test procedure and Apparatus for testing the Smolder Resistance of Materials used in Upholstered Furniture

Sample description: **VELL. ALPACA**

Declared composition: **39% Cotton-28%Alpaca-11%Polyester-9%Virgin Wool-7% Polyamide - 6% Viscose**

Conditioning of test specimen and ignition source: **24 h at 21 ± 3 °C, <55% r.h.**

Testing temperature and r.h.: **20 °C, 58 % r.h.**

Filling specification: **NON FIRE-RETARDANT polyurethane foam with a density of 28 kg/m³**

Date of test: **06.09.2017**

Type of fabric: COVER FABRIC

Specimen number	1	2	3
Total combustion of the cigarette (YES / NO)	YES	YES	YES
Time of progressive smouldering from placement of the source (min)	33	37	37
Size of the damage in the vertical direction (mm)	16	18	18
Mock-up test specimen transitions to open flaming (YES / NO)	NO	NO	NO
CIGARETTE TEST RESULT (PASS/FAIL)	PASSES	PASSES	PASSES

Cover Fabric Classification (ref. TB 117:2013)

A single mock-up test specimen fails to meet the requirements if any of the following criteria occurs:

- The mock-up test specimen continues to smolder after the 45 minute test duration;
- A vertical char length of more than 45 mm develops on the cover fabric
- The mock-up test specimen transitions to open flaming.

2. The cover fabric passes the test if three initial mock-up specimens pass the test, i.e., the cigarettes burn their full length and the mock-ups are no longer smoldering.

3. If more than one initial specimen fails, the cover fabric fails the test.

4. If any one of the three initial specimens fails, repeat the test on additional three specimens.

5. If all three additional specimens pass the test, the cover fabric passes the test. If any one of the additional three specimens fails, the cover fabric fails the test.

The following test result relate only to the ignitability of the combination of materials under the particular conditions of test.

They are not intended as a means of assessing the full potential fire hazard of the material in use.

Upholstery cover fabrics that fail the cover fabric test described in Section 1 can be used in upholstered furniture if a barrier (interliner) material that passes the test method described in Section 2 is used. When a barrier is required, the barrier material must cover all sides and top of the seating cushion(s). Exceptions: Non-reversible and non-detachable seating cushions do not require the use of the barrier material on the underside of the seating cushion.