



REPORT

Report nr.: **1600462-001**
Report date: **29-gen-16**
Acceptance code: **1600462**
Acceptance date: **22-gen-16**
Start test date: **22-gen-16**
End test date: **29-gen-16**
References: **---**

Customer code: 5485

To:
MARIO SIRTORI SPA
via Papa Giovanni XXIII 10
23845 COSTA MASNAGA (LC)
Italia

To the attention of:
sig. Sergio Sala Crist

Tel.nr: +39 031 879632
Fax.nr.: +39 031 855397

Article description: **LAMA**
Declared composition: **75% Wool - 15% Alpaca - 10% Polyamide**
End use: **Furnishing**
Typology: **Fabric**
Return: **No requested**
Sampling by customer

The results reported herein refer to the tested samples only and do not involve any product approval by Centro Tessile Serico.
This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory.

TEST	M.U.	RESULTS
------	------	---------

**14253 TEAR PROPERTIES OF FABRICS WING
SHAPED (2 directions)**

Method: UNI EN ISO 13937-3:2002+EC 1-2004

Instrument: CRE Dynamometer

Date of test: 27/01/2016

Tear force of yarns WARP - Average 75 N

Tear force of yarns WEFT - Average 74 N

Deviation from procedure -

END OF REPORT

Supervisor Head

p.i. Giovanna Baglio

Technical Head

dott. Marco Piu